

PolyOne Geon™ Vinyl Flexible C70A0 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-C70A0-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.37 g/cc	1.37 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	15 sec; ASTM D2240
	70	70	ASTM D2240
Tensile Strength at Break	9.65 MPa	1400 psi	510 mm/min; ASTM D638
Tensile Strength	4.14 MPa	600 psi	510 mm/min; ASTM D638
	@Strain 100 %	@Strain 100 %	
Elongation at Break	400 %	400 %	510 mm/min; ASTM D638
Tear Strength	28.0 kN/m	160 pli	Die C, 510 mm/min; ASTM D624
Clash Berg Modulus	0.0662 GPa	9.60 ksi	ASTM D1043
	0.310 GPa	45.0 ksi	ASTM D1043
	@Temperature -43.0 °C	@Temperature -45.4 °F	

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-40.0 °C	-40.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	168 - 177 °C	334 - 351 °F	
	188 - 199 °C	370 - 390 °F	

Descriptive Properties	Value	Comments
Agency Ratings	NSF 51	BLACK 2999, NATURAL. Max. Temp. of use = 100 degrees F.
Features	Good Adhesion	
Forms	Pellets	

Descriptive Properties	Value	Comments
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Coextrusion	
	Extrusion	
	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Construction Applications	
	Seals	
	Weatherstripping	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China