

PolyOne Geon™ Vinyl Flexible C75A0 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-C75A0-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.37 g/cc	1.37 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	67	67	15 sec; ASTM D2240
	75	75	ASTM D2240
Tensile Strength at Break	10.3 MPa	1490 psi	510 mm/min; ASTM D638
Tensile Strength	4.83 MPa @Strain 100 %	701 psi @Strain 100 %	510 mm/min; ASTM D638
Elongation at Break	380 %	380 %	510 mm/min; ASTM D638
Tear Strength	43.8 kN/m	250 pli	Die C, 510 mm/min; ASTM D624
Compression Set	25 % @Temperature 23.0 °C, Time 79200 sec	25 % @Temperature 73.4 °F, Time 22.0 hour	ASTM D395
Clash Berg Modulus	0.138 GPa	20.0 ksi	ASTM D1043
	0.310 GPa @Temperature -42.0 °C	45.0 ksi @Temperature -43.6 °F	ASTM D1043

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-40.0 °C	-40.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	174 - 179 °C	345 - 354 °F	
	188 - 199 °C	370 - 390 °F	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Agency Ratings Descriptive Properties	NSF 51 Value	BLACK 2999. Max. Temp. of use = 100 degrees F. Comments
Appearance	Opaque	
Features	Good Adhesion	
	Medium Gloss	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Coextrusion	
	Extrusion	
	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Construction Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China