

PolyOne Geon™ Vinyl Flexible K85 Natural & Black Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-K85-Natural-Black-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	15 sec; ASTM D2240
	75	75	ASTM D2240
Tensile Strength at Break	14.5 MPa	2100 psi	510 mm/min; ASTM D638
Tensile Strength	6.21 MPa	901 psi	510 mm/min; ASTM D638
	@Strain 100 %	@Strain 100 %	
Elongation at Break	380 %	380 %	510 mm/min; ASTM D638
Tear Strength	52.5 kN/m	300 pli	Die C, 510 mm/min; ASTM D624

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-43.9 °C	-47.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	174 - 179 °C	345 - 354 °F	
	185 - 196 °C	365 - 385 °F	

Descriptive Properties	Value	Comments
Additive	Biocide	
	UV Stabilizer	
Features	UV Absorbing	
Forms	Pellets	
Generic Material	PVC, Flexible	

Descriptive Properties	Value	Comments
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China