

PolyOne Geon™ Vinyl Flexible R2495A Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-R2495A-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.45 g/cc	1.45 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	82	82	15 sec; ASTM D2240
Tensile Strength at Break	1.38 MPa	200 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	280 %	280 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-20.0 °C	-4.00 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	179 - 185 °C	354 - 365 °F	

Descriptive Properties	Value	Comments
Additive	UV Stabilizer	
Features	Low Gloss	
	UV Absorbing	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
	Profile Extrusion	
Regional Availability	Africa & Middle East	

Descriptive Properties	Asia Pacific Value	Comments
	Europe	
	North America	
	South America	
Uses	Automotive Bumper	
	Hose	
	Profiles	
	Tubing	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China