

PolyOne Geon™ Vinyl Flexible R4294Y Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-R4294Y-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	86	86	15 sec; ASTM D2240
Tensile Strength at Break	19.3 MPa	2800 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	320 %	320 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-23.9 °C	-11.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	174 - 179 °C	345 - 354 °F	
	193 - 204 °C	379 - 399 °F	

Descriptive Properties	Value	Comments
Appearance	Clear/Transparent	
Features	High Clarity	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
	Injection Molding	
Regional Availability	Africa & Middle East	

Descriptive Properties	Asia Pacific Value	Comments
	Europe	
	North America	
	South America	
Uses	Automotive Applications	
	Automotive Exterior Trim	
	Furniture	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China