

## PolyOne Geon™ Vinyl Flexible Y126 White 317 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

### Material Notes:

Information provided by PolyOne

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PolyOne-Geon-Vinyl-Flexible-Y126-White-317-Polyvinyl-Chloride-Flexible-PVC-Flexible.php](http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-Y126-White-317-Polyvinyl-Chloride-Flexible-PVC-Flexible.php)

| Physical Properties | Metric    | English   | Comments  |
|---------------------|-----------|-----------|-----------|
| Specific Gravity    | 1.20 g/cc | 1.20 g/cc | ASTM D792 |

| Mechanical Properties     | Metric   | English  | Comments                       |
|---------------------------|----------|----------|--------------------------------|
| Hardness, Shore A         | 67       | 67       | 15 sec; ASTM D2240             |
| Tensile Strength at Break | 15.2 MPa | 2200 psi | Type IV, 510 mm/min; ASTM D638 |
| Elongation at Break       | 400 %    | 400 %    | Type IV, 510 mm/min; ASTM D638 |

| Thermal Properties      | Metric                     | English                     | Comments   |
|-------------------------|----------------------------|-----------------------------|------------|
| Brittleness Temperature | -38.9 °C                   | -38.0 °F                    | ASTM D746  |
| Oxygen Index            | 22 %<br>@Thickness 3.18 mm | 22 %<br>@Thickness 0.125 in | ASTM D2863 |

| Processing Properties | Metric       | English      | Comments |
|-----------------------|--------------|--------------|----------|
| Melt Temperature      | 177 - 182 °C | 351 - 360 °F |          |
|                       | 193 - 204 °C | 379 - 399 °F |          |

| Descriptive Properties | Value                                        | Comments |
|------------------------|----------------------------------------------|----------|
| Features               | Good Adhesion                                |          |
|                        | High Flow                                    |          |
| Forms                  | Pellets                                      |          |
| Generic Material       | PVC, Flexible                                |          |
| Generic Name           | Polyvinyl Chloride, Flexible (PVC, Flexible) |          |
| Processing Method      | Coextrusion                                  |          |
|                        | Extrusion                                    |          |

| Descriptive Properties | Value                | Comments |
|------------------------|----------------------|----------|
|                        | Injection Molding    |          |
| Regional Availability  | Africa & Middle East |          |
|                        | Asia Pacific         |          |
|                        | Europe               |          |
|                        | North America        |          |
|                        | South America        |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China