

PolyOne Geon™ Vinyl Packaging XPL 293 FROST 1733 Polyvinyl Chloride, Rigid (PVC, Rigid)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Rigid Grade

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Packaging-XPL-293-FROST-1733-Polyvinyl-Chloride-Rigid-PVC-Rigid.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.33 g/cc	1.33 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	77	77	ASTM D2240
Tensile Strength, Yield	49.8 MPa	7220 psi	Type I, 5.1 mm/min; ASTM D638
Izod Impact, Notched	1.20 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	2.25 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Injection Molded; ASTM D256A

Processing Properties	Metric	English	Comments
Mold Temperature	202 - 207 °C	396 - 405 °F	Blow Molding

Descriptive Properties	Value	Comments
Agency Ratings	FDA Food Contact, Unspecified Rating	
Appearance	Clear/Transparent	
Features	Food Contact Acceptable	
	High Impact Resistance	
Forms	Pellets	
Generic Material	PVC, Rigid	
Generic Name	Polyvinyl Chloride, Rigid (PVC, Rigid)	
Processing Method	Blow Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	

Descriptive Properties	Value	Comments
	North America	
	South America	
Uses	Bottles	
	Packaging	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China