

PolyOne Geon™ Vinyl Wire & Cable W1201 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Typical Properties of Molded Slab (0.075); Not to be Construed as Specifications. Provisional Product Information - Physical and Mechanical properties based on initial production. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Wire-Cable-W1201-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	56	56	15 sec; ASTM D2240
Tensile Strength, Yield	17.2 MPa	2490 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	290 %	290 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-20.0 °C	-4.00 °F	ASTM D746
Oxygen Index	30 % @Thickness 3.18 mm	30 % @Thickness 0.125 in	ASTM D2863

Processing Properties	Metric	English	Comments
Melt Temperature	188 - 193 °C	370 - 379 °F	

Descriptive Properties	Value	Comments
Additive	Lead Stabilizer	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
	Injection Molding	
Regional Availability	Africa & Middle East	

Descriptive Properties	Value	Comments
	Europe	
	North America	
	South America	
Retention of Tensile Elongation	85%	121°C, 762.0 µm; 168 hr, UL Standard
Uses	Wire & Cable Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China