

PolyOne Geon™ Vinyl Wire & Cable W1349L-xx09FRD Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Typical Properties of Molded Slab (0.075); Not to be Construed as Specifications. Provisional Product Information - Physical and Mechanical properties based on initial production. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Wire-Cable-W1349L-xx09FRD-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.32 g/cc	1.32 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	45	45	15 sec; ASTM D2240
Tensile Strength at Break	24.1 MPa	3500 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	200 %	200 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	60.0 °C	140 °F	UL Temperature Rating
Brittleness Temperature	-7.00 °C	19.4 °F	ASTM D746
Oxygen Index	30 % @Thickness 1.91 mm	30 % @Thickness 0.0752 in	ASTM D2863

Processing Properties	Metric	English	Comments
Melt Temperature	182 - 191 °C	360 - 376 °F	

Descriptive Properties	Value	Comments
Agency Ratings	UL 444	
Features	Flame Retardant	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion Coating	

Descriptive Properties	Value & Middle East	Comments
	Asia Pacific	
	Europe	
	North America	
	South America	
Retention of Tensile Elongation	98%	100°C, 1.91 mm; 168 hr, UL Standard
Retention of Tensile Strength	88%	100°C, 1.91 mm; 168 hr, UL Standard
RoHS Compliance	RoHS Compliant	
Uses	Communication Wire Insulation	
	Wire & Cable Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China