

PolyOne Geon™ Vinyl Wire & Cable W9400L Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Typical Properties of Molded Slab (0.075); Not to be Construed as Specifications. Provisional Product Information - Physical and Mechanical properties based on initial production. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Wire-Cable-W9400L-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	35	35	15 sec; ASTM D2240
Tensile Strength, Yield	20.0 MPa	2900 psi	Type IV, 510 mm/min; ASTM D638
Elongation at Break	340 %	340 %	Type IV, 510 mm/min; ASTM D638

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	105 °C	221 °F	UL Temperature Rating
Brittleness Temperature	-18.9 °C	-2.02 °F	ASTM D746
Flammability, UL94	V-0 @Thickness 1.50 mm	V-0 @Thickness 0.0591 in	ALL; UL 94
Oxygen Index	30 % @Thickness 3.18 mm	30 % @Thickness 0.125 in	ASTM D2863

Processing Properties	Metric	English	Comments
Melt Temperature	182 - 188 °C	360 - 370 °F	

Descriptive Properties	Value	Comments
Features	Flame Retardant	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	

Processing Method Descriptive Properties	Extrusion Value	Comments
Injection Molding		
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Retention of Tensile Elongation	90%	136°C, 508.0 µm; 168 hr, UL Standard
Retention of Tensile Strength	110%	136°C, 508.0 µm; 168 hr, UL Standard
RoHS Compliance	RoHS Compliant	
Uses	Wire & Cable Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China