

PolyOne Nymax™ GF 600 A 33 Black 28 V Polyamide 6 (Nylon 6)

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

The Nymax® GF 600 Series of glass fiber-reinforced nylon 6 compounds have been specifically engineered for applications requiring high stiffness, tensile strength, and toughness, while providing enhanced surface appearance versus nylon 6/6 compounds. These materials are available in a broad range of reinforcement levels depending upon stiffness characteristics desired and have been formulated to offer ease of processing in most standard thermoplastic processing equipment. Molded Test Bars: Dry as Molded Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Nymax-GF-600-A-33-Black-28-V-Polyamide-6-Nylon-6.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.37 g/cc	1.37 g/cc	ASTM D792
Water Absorption	1.2 %	1.2 %	@ 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	165 MPa	23900 psi	Type I, 5.1 mm/min; ASTM D638
Tensile Strength, Yield	165 MPa	23900 psi	Type I, 5.1 mm/min; ASTM D638
Elongation at Yield	3.0 %	3.0 %	Type I, 5.1 mm/min; ASTM D638
Tensile Modulus	8.27 GPa	1200 ksi	ASTM D638
Flexural Strength	234 MPa	33900 psi	ASTM D790
Flexural Modulus	8.27 GPa	1200 ksi	ASTM D790
Izod Impact, Notched	1.10 J/cm @Thickness 3.18 mm, Temperature 23.0 °C	2.06 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Injection Molded; ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	204 °C @Thickness 3.18 mm	399 °F @Thickness 0.125 in	Annealed; ASTM D648

Processing Properties	Metric	English	Comments
Mold Temperature	48.9 - 93.3 °C	120 - 200 °F	
Drying Temperature	82.2 °C	180 °F	

Dry Time Processing Properties	4.00 hour Metric	4.00 hour English	Comments
-----------------------------------	---------------------	----------------------	----------

Descriptive Properties	Value	Comments
Appearance	Black	
Automotive Specifications	FORD ESB-M4D133-A	
Features	General Purpose	
	Good Weather Resistance	
Filler / Reinforcement	Glass Fiber Reinforcement, 33% Filler by Weight	
Forms	Pellets	
Generic Material	Nylon 6	
Generic Name	Polyamide 6 (Nylon 6)	
Processing Method	Injection Molding	
Regional Availability	North America	
	South America	
Uses	Automotive Applications	
	Construction Applications	
	Consumer Applications	
	General Purpose	
	Industrial Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China