

PolyOne OnFlex™ HFFR 361-0190 Thermoplastic Elastomer (TPE)

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

OnFlex™ HFFR 361-0190 is a non-halogen flame retardant material designed for injection molding applications. New Product. Commercial specifications have not been established. - UL 94 HB compliantPurge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-OnFlex-HFFR-361-0190-Thermoplastic-Elastomer-TPE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.01 g/cc	1.01 g/cc	ASTM D792
Viscosity	105000 cP @Shear Rate 1340 1/s, Temperature 200 °C	105000 cP @Shear Rate 1340 1/s, Temperature 392 °F	ASTM D3835
Maximum Moisture Content	0.020	0.020	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	92	92	10 sec; ASTM D2240
Tensile Strength at Break	12.2 MPa @Temperature 23.0 °C	1770 psi @Temperature 73.4 °F	Die C2 hr; ASTM D412
Elongation at Break	220 % @Temperature 23.0 °C	220 % @Temperature 73.4 °F	Die C2 hr; ASTM D412
Tear Strength	57.2 kN/m	326 pli	ASTM D624

Thermal Properties	Metric	English	Comments
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	UL 94
	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	UL 94

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	182 - 193 °C	360 - 379 °F	
Middle Barrel Temperature	210 - 227 °C	410 - 441 °F	
Front Barrel Temperature	227 - 238 °C	441 - 460 °F	

Processing Properties	Metric	English	Comments
	113.3 °C	238 °F	
Drying Temperature	70.0 °C	158 °F	
Dry Time	2.00 - 3.00 hour	2.00 - 3.00 hour	

Descriptive Properties	Value	Comments
Agency Ratings	UL 94 .QMFZ2.E76261	
Appearance	Black	
Forms	Pellets	
Generic Material	TPE	
Generic Name	Thermoplastic Elastomer (TPE)	
Injection Rate	Slow-Moderate	
Manufacturer / Supplier	GLS Thermoplastic Elastomers	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Connectors	
	Plugs	
	Wire & Cable Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China