

PolyOne OnFlex™ S HF 80A-3S1986 Thermoplastic Elastomer (TPE)

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

OnFlex™-S HF thermoplastic elastomer compounds are based on hydrogenated styrenic block copolymers. This range of compounds utilize a unique, patent pending halogen free flame retardancy system. Furthermore, OnFlex™-S HF compounds offer good mechanical properties, compliance with UL94 V-0, good LOI values, wide hardness range, good processability, and excellent UV stability. Properties are measured using injection molded plaques. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-OnFlex-S-HF-80A-3S1986-Thermoplastic-Elastomer-TPE.php

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0383 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80	80	ISO 868
Tensile Strength at Break	5.50 MPa	798 psi	ISO 37
Tensile Stress	3.00 MPa	435 psi	ISO 37
	@Strain 100 %	@Strain 100 %	
	4.20 MPa	609 psi	ISO 37
	@Strain 300 %	@Strain 300 %	
Elongation at Break	420 %	420 %	ISO 37
Tear Strength	35.0 kN/m	200 pli	ISO 34-1
Compression Set	31 %	31 %	ISO 815
	@Temperature 23.0 °C, Time 259000 sec	@Temperature 73.4 °F, Time 72.0 hour	
	50 %	50 %	ISO 815
	@Temperature 70.0 °C, Time 79200 sec	@Temperature 158 °F, Time 22.0 hour	
	81 %	81 %	ISO 815
	@Temperature 100 °C, Time 79200 sec	@Temperature 212 °F, Time 22.0 hour	

Thermal Properties	Metric	English	Comments
Flammability, UL94	V-0	V-0	UL 94
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Thermal Properties	Metric	English	Comments
Glow Wire Test	725 °C	1340 °F	Ignition Temperature; IEC 60695-2-13
	@Thickness 2.00 mm	@Thickness 0.0787 in	
	960 °C	1760 °F	Flammability Index; IEC 60695-2-12
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	550 V	550 V	IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	160 - 180 °C	320 - 356 °F	
Mold Temperature	30.0 - 50.0 °C	86.0 - 122 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	2.00 hour	2.00 hour	

Descriptive Properties	Value	Comments
Features	Flame Retardant	
Forms	Pellets	
Generic Material	TPE	
Generic Material Type	Styrenic Thermoplastic Elastomer (TES)	
Generic Name	Thermoplastic Elastomer (TPE)	
Injection Rate	Moderate-Fast	
Manufacturer / Supplier	GLS Thermoplastic Elastomers	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	South America	
RoHS Compliance	RoHS Compliant	
Uses	Automotive Applications	

Descriptive Properties	Valueless Equipment	Comments
	Electrical/Electronic Applications	
	General Purpose	
	Industrial Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China