

PolyOne OnFlex™ S KE 70A-3S1726 Thermoplastic Elastomer (TPE)

Category : Polymer , Thermoplastic , Elastomer , TPE

Material Notes:

OnFlex™-S KE thermoplastic elastomer compounds are based on hydrogenated styrenic block copolymers. This range of compounds are specially compatibilized to provide excellent adhesion to a variety polar substrates including PC, ABS, PC/ABS, ASA and PVC. OnFlex-S KE compounds can be processed by 2K molding or overmoulding, insert moulding or co-extrusion. In addition to this OnFlex-S KE compounds are formulated to provide good compression set performance, even at elevated temperatures, good processability, a wide hardness range, low temperature flexibility, good scratch resistance, good colourability and surface appearance, and excellent mechanical properties. Properties are measured using injection molded plaques. Compression Set values are for parts annealed for 24 hours at 100°C. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-OnFlex-S-KE-70A-3S1726-Thermoplastic-Elastomer-TPE.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in³	ISO 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	ISO 868
Tensile Strength at Break	11.3 MPa	1640 psi	ISO 37
Tensile Stress	3.00 MPa	435 psi	ISO 37
	@Strain 100 %	@Strain 100 %	
	5.80 MPa	841 psi	ISO 37
	@Strain 300 %	@Strain 300 %	
Elongation at Break	500 %	500 %	ISO 37
Compression Set	29 %	29 %	ISO 815
	@Temperature 23.0 °C, Time 259000 sec	@Temperature 73.4 °F, Time 72.0 hour	
	50 %	50 %	ISO 815
	@Temperature 70.0 °C, Time 79200 sec	@Temperature 158 °F, Time 22.0 hour	
	73 %	73 %	ISO 815
	@Temperature 100 °C, Time 79200 sec	@Temperature 212 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Melt Temperature			

Processing Properties	200 - 230 °C Metric	392 - 446 °F English	Comments
Mold Temperature	20.0 - 40.0 °C	68.0 - 104 °F	
Drying Temperature	100 °C	212 °F	
Dry Time	2.00 hour	2.00 hour	

Descriptive Properties	Value	Comments
Features	Good Adhesion	
	Scratch Resistant	
Forms	Pellets	
Generic Material	TPE	
Generic Material Type	Styrenic Thermoplastic Elastomer (TES)	
Generic Name	Thermoplastic Elastomer (TPE)	
Injection Rate	Slow-Moderate	
Manufacturer / Supplier	GLS Thermoplastic Elastomers	
Processing Method	Coextrusion	
	Multi Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
RoHS Compliance	RoHS Compliant	
Uses	Automotive Applications	
	Consumer Applications	
	Industrial Applications	
	Overmolding	
	Power/Other Tools	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China