

Polykemi AB POLYasa 2008F UV-stabilized, High Flow ASA

Category : Polymer , Thermoplastic , ASA Polymer

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-POLYasa-2008F-UV-stabilized-High-Flow-ASA.php

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	With Flow; ISO 2577
	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	Across Flow; ISO 2577
Melt Index of Compound	20 g/10 min @Load 10.0 kg, Temperature 220 °C	20 g/10 min @Load 22.0 lb, Temperature 428 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 50.0 MPa	<= 7250 psi	ISO/R527
Elongation at Yield	5.5 %	5.5 %	ISO/R527
Flexural Strength	<= 86.0 MPa	<= 12500 psi	ISO 178
Flexural Modulus	2.50 GPa @Temperature 23.0 °C	363 ksi @Temperature 73.4 °F	ISO 178
Charpy Impact, Notched	0.500 J/cm ² @Temperature -20.0 °C	2.38 ft-lb/in ² @Temperature -4.00 °F	ISO 179
	0.800 J/cm ² @Temperature 23.0 °C	3.81 ft-lb/in ² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	95.0 °C	203 °F	120°C/h; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	86.0 °C	187 °F	120°C/h; ISO 75/1
Vicat Softening Point	95.0 °C @Load 5.001 kg	203 °F @Load 11.03 lb	50°C/h; ISO 306
	103 °C	217 °F	

Thermal Properties	Metric @Load 1.00 kg	English @Load 2.21 lb	50°C/h- ISO 306 Comments
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
Glow Wire Test	650 °C @Thickness 2.00 mm	1200 °F @Thickness 0.0787 in	IEC 695-2-1

Processing Properties	Metric	English	Comments
Melt Temperature	190 - 230 °C	374 - 446 °F	
Mold Temperature	60.0 - 80.0 °C	140 - 176 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	2 - 4 hour	2 - 4 hour	in circulation dryer
	2 - 4 hour	2 - 4 hour	in fresh-air dryer
	2 - 4 hour	2 - 4 hour	in desiccant air dryer
Injection Pressure	90.0 - 150 MPa	13100 - 21800 psi	
Back Pressure	1.00 - 1.50 MPa	145 - 218 psi	

Descriptive Properties	Value	Comments
Holding Pressure ()	20-40	% of injection pressure
Injection Speed ()	High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China