

Polykemi AB POLYblend 45FS GK25 PC/ABS-Blend, Glass Fiber reinforced

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Glass Fiber Filled , Polycarbonate (PC)

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-POLYblend-45FS-GK25-PCABS-Blend-Glass-Fiber-reinforced.php

Physical Properties	Metric	English	Comments
Density	1.24 g/cc	0.0448 lb/in ³	ISO 1183
Filler Content	25 %	25 %	±2%; Polykemi

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 27.0 MPa	<= 3920 psi	ISO/R527
Elongation at Break	5.0 %	5.0 %	ISO/R527
Flexural Strength	<= 57.0 MPa	<= 8270 psi	ISO 178
Flexural Modulus	3.00 GPa @Temperature 23.0 °C	435 ksi @Temperature 73.4 °F	ISO 178
Charpy Impact, Notched	0.300 J/cm ² @Temperature 23.0 °C	1.43 ft-lb/in ² @Temperature 73.4 °F	ISO 179
	0.300 J/cm ² @Temperature -20.0 °C	1.43 ft-lb/in ² @Temperature -4.00 °F	ISO 179

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	101 °C	214 °F	120°C/h; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	95.0 °C	203 °F	120°C/h; ISO 75/1
Vicat Softening Point	100 °C @Load 5.001 kg	212 °F @Load 11.03 lb	50°C/h; ISO 306
	108 °C @Load 1.00 kg	226 °F @Load 2.21 lb	50°C/h; ISO 306

Processing Properties	Metric	English	Comments
Melt Temperature	240 - 280 °C	464 - 536 °F	

Processing Properties	Metric ^{70.0 - 100 °C}	English ^{158 - 212 °F}	Comments
Drying Temperature	100 - 110 °C	212 - 230 °F	
Dry Time	2 - 8 hour	2 - 8 hour	in circulation dryer
	2 - 8 hour	2 - 8 hour	in fresh-air dryer
	2 - 8 hour	2 - 8 hour	in desiccant air dryer
Injection Pressure	90.0 - 150 MPa	13100 - 21800 psi	
Back Pressure	0.500 - 1.50 MPa	72.5 - 218 psi	

Descriptive Properties	Value	Comments
Holding Pressure ()	20-50	% of injection pressure
Injection Speed ()	High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China