

Polykemi AB POLYfill PP HJ752 UV Polypropylene/Elastomer, Mineral Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Talc Filler

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-POLYfill-PP-HJ752-UV-PolypropyleneElastomer-Mineral-Reinforced.php

Physical Properties	Metric	English	Comments
Density	0.980 g/cc	0.0354 lb/in ³	ISO 1183
Filler Content	15 %	15 %	±2%; Polykemi
Linear Mold Shrinkage	0.0080 - 0.010 cm/cm	0.0080 - 0.010 in/in	With Flow; ISO 2577
	0.0080 - 0.010 cm/cm	0.0080 - 0.010 in/in	Across Flow; ISO 2577
Melt Index of Compound	14 g/10 min @Load 2.16 kg, Temperature 230 °C	14 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 22.0 MPa	<= 3190 psi	ISO/R527
Elongation at Break	167 %	167 %	ISO/R527
Elongation at Yield	9.0 %	9.0 %	ISO/R527
Flexural Strength	<= 32.0 MPa	<= 4640 psi	ISO 178
Flexural Modulus	1.70 GPa @Temperature 23.0 °C	247 ksi @Temperature 73.4 °F	ISO 178
Charpy Impact Unnotched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 179
	NB @Temperature -20.0 °C	NB @Temperature -4.00 °F	ISO 179
Charpy Impact, Notched	0.500 J/cm ² @Temperature -20.0 °C	2.38 ft-lb/in ² @Temperature -4.00 °F	ISO 179
	2.30 J/cm ² @Temperature 23.0 °C	10.9 ft-lb/in ² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
CTE, linear	55.0 - 65.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	30.6 - 36.1 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	Polykemi
Deflection Temperature at 0.46 MPa (66 psi)	100 $^{\circ}\text{C}$	212 $^{\circ}\text{F}$	120 $^{\circ}\text{C}/\text{h}$; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	57.0 $^{\circ}\text{C}$	135 $^{\circ}\text{F}$	120 $^{\circ}\text{C}/\text{h}$; ISO 75/1
Vicat Softening Point	53.0 $^{\circ}\text{C}$	127 $^{\circ}\text{F}$	50 $^{\circ}\text{C}/\text{h}$; ISO 306
	@Load 5.001 kg	@Load 11.03 lb	
	130 $^{\circ}\text{C}$	266 $^{\circ}\text{F}$	50 $^{\circ}\text{C}/\text{h}$; ISO 306
	@Load 1.00 kg	@Load 2.21 lb	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China