

Polykemi AB POLYfill PPH FX801020 Polypropylene Homopolymer, Glass Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Glass Fiber Filler

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-POLYfill-PPH-FX801020-Polypropylene-Homopolymer-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	ISO 1183
Filler Content	30 %	30 %	±2%; Polykemi
Linear Mold Shrinkage	0.0080 cm/cm	0.0080 in/in	With Flow; ISO 2577
	0.012 cm/cm	0.012 in/in	Across Flow; ISO 2577
Melt Index of Compound	8.0 g/10 min @Load 2.16 kg, Temperature 230 °C	8.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 40.0 MPa	<= 5800 psi	ISO/R527
Elongation at Break	5.0 %	5.0 %	ISO/R527
Flexural Strength	<= 55.0 MPa	<= 7980 psi	ISO 178
Flexural Modulus	3.00 GPa @Temperature 23.0 °C	435 ksi @Temperature 73.4 °F	ISO 178
Charpy Impact, Notched	0.300 J/cm ² @Temperature 23.0 °C	1.43 ft-lb/in ² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
Glow Wire Test	750 °C @Thickness 2.00 mm	1380 °F @Thickness 0.0787 in	IEC 695-2-1

Processing Properties	Metric	English	Comments

Melt Temperature Processing Properties	205 - 260 °C Metric	401 - 500 °F English	Comments
Mold Temperature	40.0 - 80.0 °C	104 - 176 °F	
Drying Temperature	70.0 - 80.0 °C	158 - 176 °F	
Dry Time	2 - 4 hour	2 - 4 hour	in circulation dryer
	2 - 4 hour	2 - 4 hour	in desiccant air dryer
Injection Pressure	40.0 - 110 MPa	5800 - 16000 psi	
Back Pressure	1.00 - 2.00 MPa	145 - 290 psi	

Descriptive Properties	Value	Comments
Holding Pressure ()	20-40	% of injection pressure
Injection Speed ()	High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China