

Polykemi AB SCANAMID 66 A12^ Q40 Nylon 66, Mineral Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 40% Mineral Filled

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-SCANAMID-66-A12-Q40-Nylon-66-Mineral-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.47 g/cc	0.0531 lb/in³	ISO 1183
Filler Content	40 %	40 %	±2%; Polykemi
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	With Flow; ISO 2577
	0.012 cm/cm	0.012 in/in	Across Flow; ISO 2577

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	80 @Time 15.0 sec	80 @Time 0.00417 hour	ASTM D2240
Tensile Strength at Break	<= 90.0 MPa	<= 13100 psi	ISO/R527
Elongation at Break	5.0 %	5.0 %	ISO/R527
Flexural Strength	<= 135 MPa	<= 19600 psi	ISO 178
Flexural Modulus	5.00 GPa @Temperature 23.0 °C	725 ksi @Temperature 73.4 °F	ISO 178
Charpy Impact, Notched	0.500 J/cm² @Temperature -20.0 °C	2.38 ft-lb/in² @Temperature -4.00 °F	ISO 179
	0.800 J/cm² @Temperature 23.0 °C	3.81 ft-lb/in² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	120°C/h; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	215 °C	419 °F	120°C/h; ISO 75/1
Vicat Softening Point	>= 230 °C @Load 5.001 kg	>= 446 °F @Load 11.03 lb	50°C/h; ISO 306

Thermal Properties	HB Metric	HB English	Comments
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Glow Wire Test	650 °C	1200 °F	IEC 695-2-1
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China