

Polykemi AB SCANMID 6 B11^ Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Information provided by Polykemi AB

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polykemi-AB-SCANMID-6-B11-Nylon-6.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in³	ISO 1183
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	With Flow; ISO 2577
	0.014 cm/cm	0.014 in/in	Across Flow; ISO 2577

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 75.0 MPa	<= 10900 psi	ISO/R527
Elongation at Yield	4.0 %	4.0 %	ISO/R527
Flexural Strength	<= 95.0 MPa	<= 13800 psi	ISO 178
Flexural Modulus	2.60 GPa	377 ksi	ISO 178
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.900 J/cm²	4.28 ft-lb/in²	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	180 °C	356 °F	120°C/h; ISO 75/1
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	120°C/h; ISO 75/1
Vicat Softening Point	200 °C	392 °F	50°C/h; ISO 306
	@Load 5.001 kg	@Load 11.03 lb	
Flammability, UL94	V-2	V-2	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Glow Wire Test	750 °C	1380 °F	IEC 695-2-1
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China