

Polymer Resources ABS-G5-[color]-3 ABS, 5% Glass Reinforced, UV-stabilized

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 10% Glass Fiber Filled

Material Notes:

Acrylonitrile Butadiene Styrene, 5% Glass Reinforced, UV-stabilized
Process: Injection Molding
Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples.
Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-ABS-G5-color-3-ABS-5-Glass-Reinforced-UV-stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.08 g/cc	1.08 g/cc	ASTM D792
Linear Mold Shrinkage	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	ASTM D955
Melt Flow	0.50 - 5.0 g/10 min @Load 3.80 kg, Temperature 230 °C	0.50 - 5.0 g/10 min @Load 8.38 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	42.7 MPa	6200 psi	ASTM D638
Tensile Strength, Yield	45.5 MPa	6600 psi	ASTM D638
Flexural Strength	65.5 MPa	9500 psi	ASTM D790
Flexural Modulus	2.90 GPa	420 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm @Temperature 22.8 °C	1.50 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	93.3 °C	200 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	87.8 °C	190 °F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	191 - 199 °C	375 - 390 °F	
Middle Barrel Temperature	210 - 221 °C	410 - 430 °F	
Front Barrel Temperature	210 - 227 °C	410 - 440 °F	
Melt Temperature	227 - 238 °C	440 - 460 °F	

Mold Temperature Processing Properties	48.9 - 60.0 °C Metric	120 - 140 °F English	Comments
Drying Temperature	79.4 - 85.0 °C	175 - 185 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Vent	0.001	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China