

Polymer Resources NY66-MD02 Nylon, 2% Molybdenum disulfide for lubrication and wear (DAM)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, MoS2 Filled

Material Notes:

Process: Injection Molding Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples.

Nylon grades are tested dry as molded (DAM). Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-NY66-MD02-Nylon-2-Molybdenum-disulfide-for-lubrication-and-wear-DAM.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.012 - 0.018 cm/cm	0.012 - 0.018 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	82.7 MPa	12000 psi	ASTM D638
Tensile Strength, Yield	82.7 MPa	12000 psi	ASTM D638
Flexural Strength	103 MPa	15000 psi	ASTM D790
Flexural Modulus	3.62 GPa	525 ksi	ASTM D790
Izod Impact, Notched	0.427 J/cm	0.800 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	218 °C	425 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	82.2 °C	180 °F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	266 - 277 °C	510 - 530 °F	
Middle Barrel Temperature	271 - 282 °C	520 - 540 °F	
Front Barrel Temperature	277 - 288 °C	530 - 550 °F	
Melt Temperature	277 - 293 °C	530 - 560 °F	
Mold Temperature	65.6 - 93.3 °C	150 - 200 °F	
Drying Temperature	73.9 - 85.0 °C	165 - 185 °F	

Dry Time Processing Properties	3 - 4 hour Metric	3 - 4 hour English	Comments
--	-------------------------------------	--------------------------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China