

Polymer Resources PCSF-FRG30 Polycarbonate, 30% Glass Reinforced Structural Foam Grade

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, 30% Glass Filled , Polycarbonate, Foam Grade, Glass Filled , Polycarbonate, Glass Fiber Filled, Flame Retardant

Material Notes:

Polycarbonate, 30% Glass Reinforced Structural Foam Grade Features: • Flame Retardant • Foamable • Self Extinguishing Process: Foam

Molding Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-PCSF-FRG30-Polycarbonate-30-Glass-Reinforced-Structural-Foam-Grade.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.43 g/cc	1.43 g/cc	ASTM D792
Linear Mold Shrinkage	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	ASTM D955
Melt Flow	3.0 - 12 g/10 min @Load 1.20 kg, Temperature 300 °C	3.0 - 12 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	124 MPa	18000 psi	ASTM D638
Tensile Strength, Yield	124 MPa	18000 psi	ASTM D638
Flexural Strength	152 MPa	22000 psi	ASTM D790
Flexural Modulus	6.89 GPa	1000 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm @Temperature 22.8 °C	1.50 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	152 °C	305 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	146 °C	295 °F	ASTM D648
Flammability, UL94	V-0 @Thickness 6.00 mm	V-0 @Thickness 0.236 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	254 - 266 °C	490 - 510 °F	

Processing Properties	Metric	English	Comments
Front Barrel Temperature	293 - 310 °C	560 - 590 °F	
Melt Temperature	288 - 316 °C	550 - 600 °F	
Mold Temperature	71.1 - 104 °C	160 - 220 °F	
Drying Temperature	118 - 124 °C	245 - 255 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China