

Polymer Resources PC/TP-GP2-[color]-UV PC/Polyester Alloy, UV-stabilized

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/PET Polyester Blend , Polyester, TP

Material Notes:

High Impact, Excellent Chemical Resistance, UV-stabilized
 Process: Injection Molding
 Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples.
 Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-PCTP-GP2-color-UV-PCPolyester-Alloy-UV-stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.22 g/cc	1.22 g/cc	ASTM D792
Linear Mold Shrinkage	0.0060 - 0.0090 cm/cm	0.0060 - 0.0090 in/in	ASTM D955
Melt Flow	6.0 - 12 g/10 min @Load 2.16 kg, Temperature 265 °C	6.0 - 12 g/10 min @Load 4.76 lb, Temperature 509 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	50.3 MPa	7300 psi	ASTM D638
Tensile Strength, Yield	51.7 MPa	7500 psi	ASTM D638
Flexural Strength	74.5 MPa	10800 psi	ASTM D790
Flexural Modulus	2.07 GPa	300 ksi	ASTM D790
Izod Impact, Notched	4.27 J/cm @Temperature -40.0 °C	8.00 ft-lb/in @Temperature -40.0 °F	ASTM D256
	8.54 J/cm @Temperature 22.8 °C	16.0 ft-lb/in @Temperature 73.0 °F	ASTM D256
Gardner Impact	36.2 J	26.7 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	98.9 °C	210 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	93.3 °C	200 °F	ASTM D648
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	
	HB	HB	

Thermal Properties	@Thickness 3.00 mm Metric	@Thickness 0.118 in English	Comments
Processing Properties	Metric	English	Comments
Rear Barrel Temperature	249 - 271 °C	480 - 520 °F	
Middle Barrel Temperature	254 - 277 °C	490 - 530 °F	
Front Barrel Temperature	260 - 282 °C	500 - 540 °F	
Melt Temperature	246 - 274 °C	475 - 525 °F	
Mold Temperature	65.6 - 87.8 °C	150 - 190 °F	
Drying Temperature	104 - 110 °C	220 - 230 °F	
Dry Time	4.00 - 6.00 hour	4.00 - 6.00 hour	

Descriptive Properties	Value	Comments
Vent	0.0015	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China