

Polymer Resources PPX-G10HF Modified-PPO, 10% Glass Reinforced, High Flow

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polyphenylene Ether, 10% Glass Filled

Material Notes:

Modified-Polyphenylene Oxide, 10% Glass Reinforced, High Flow Process: Injection Molding Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-PPX-G10HF-Modified-PPO-10-Glass-Reinforced-High-Flow.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.12 g/cc	1.12 g/cc	ASTM D792
Linear Mold Shrinkage	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	ASTM D955
Melt Flow	5.0 - 10 g/10 min @Load 11.6 kg, Temperature 250 °C	5.0 - 10 g/10 min @Load 25.6 lb, Temperature 482 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	68.9 MPa	10000 psi	ASTM D638
Tensile Strength, Yield	68.9 MPa	10000 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	96.5 MPa	14000 psi	ASTM D790
Flexural Modulus	3.65 GPa	529 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm @Temperature -30.0 °C	1.00 ft-lb/in @Temperature -22.0 °F	ASTM D256
	0.801 J/cm @Temperature 22.8 °C	1.50 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	127 °C	260 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	122 °C	252 °F	ASTM D648
Vicat Softening Point	135 °C	275 °F	120°C/h, 50 N; ASTM D1525
Flammability, UL94	HB	HB	

Thermal Properties	@Thickness 1.59 mm Metric	@Thickness 0.0626 in English	Comments
	HB	HB	
	@Thickness 3.17 mm	@Thickness 0.125 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	260 - 304 °C	500 - 580 °F	
Middle Barrel Temperature	271 - 310 °C	520 - 590 °F	
Front Barrel Temperature	282 - 316 °C	540 - 600 °F	
Melt Temperature	288 - 316 °C	550 - 600 °F	
Mold Temperature	71.1 - 104 °C	160 - 220 °F	
Drying Temperature	104 - 110 °C	220 - 230 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Vent	0.0015	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China