

Polymer Resources PPX-G30 Modified PPO, 30% Glass Reinforced (Unverified Data**)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polyphenylene Ether, 30% Glass Filled

Material Notes:

Process: Injection Molding Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples.

Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-PPX-G30-Modified-PPO-30-Glass-Reinforced-nbspUnverified-Data.php

Physical Properties	Metric	English	Comments
Density	1.28 g/cc	0.0462 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	ASTM D955
Melt Flow	1.0 - 4.0 g/10 min	1.0 - 4.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	103 MPa	15000 psi	ASTM D638
Tensile Strength, Yield	103 MPa	15000 psi	ASTM D638
Flexural Strength	131 MPa	19000 psi	ASTM D790
Flexural Modulus	6.89 GPa	1000 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm	1.50 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	149 °C	300 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	143 °C	290 °F	ASTM D648
Flammability, UL94	HB	HB	1/8 in
	HB	HB	1/16 in

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	260 - 304 °C	500 - 580 °F	
Middle Barrel Temperature	271 - 310 °C	520 - 590 °F	
Front Barrel Temperature	282 - 316 °C	540 - 600 °F	
Melt Temperature	293 - 316 °C	560 - 600 °F	

Processing Properties	Metric	English	Comments
Mold Temperature	82.2 - 116 °C	180 - 240 °F	
Drying Temperature	104 - 110 °C	220 - 230 °F	
Dry Time	3 - 4 hour	3 - 4 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China