

Polymer Resources PPX-GP2 Modified-PPO, General Purpose

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polyphenylene Ether, Molded

Material Notes:

Modified-Polyphenylene Oxide, General Purpose, 250F HDT
 Process: Injection Molding
 Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-PPX-GP2-Modified-PPO-General-Purpose.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	6.0 - 10 g/10 min @Load 11.6 kg, Temperature 250 °C	6.0 - 10 g/10 min @Load 25.6 lb, Temperature 482 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength at Break	53.4 MPa	7750 psi	ASTM D638
Tensile Strength, Yield	56.9 MPa	8250 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Flexural Strength	79.3 MPa	11500 psi	ASTM D790
Flexural Modulus	2.34 GPa	340 ksi	ASTM D790
Izod Impact, Notched	1.33 J/cm @Temperature -30.0 °C	2.50 ft-lb/in @Temperature -22.0 °F	ASTM D256
	2.14 J/cm @Temperature 22.8 °C	4.00 ft-lb/in @Temperature 73.0 °F	ASTM D256
Charpy Impact, Notched	1.47 J/cm ² @Temperature 22.8 °C	7.00 ft-lb/in ² @Temperature 73.0 °F	ISO 179/1eA
Gardner Impact	16.9 J	12.5 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	121 °C	250 °F	ASTM D648

Deflection Temperature at 1.8 MPa (150 psi) Thermal Properties	116 °C Metric	240 °F English	ASTM D648 Comments
Flammability, UL94	HB	HB	
	@Thickness 1.59 mm	@Thickness 0.0626 in	
	HB	HB	
	@Thickness 3.17 mm	@Thickness 0.125 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	249 - 299 °C	480 - 570 °F	
Middle Barrel Temperature	260 - 304 °C	500 - 580 °F	
Front Barrel Temperature	271 - 310 °C	520 - 590 °F	
Melt Temperature	282 - 310 °C	540 - 590 °F	
Mold Temperature	71.1 - 93.3 °C	160 - 200 °F	
Drying Temperature	104 - 110 °C	220 - 230 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Vent	0.0015	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China