

Polymer Resources PPX-SF2 Modified PPO, Structural Foam Grade, Standard Flow (Unverified Data**)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polyphenylene Ether, Molded

Material Notes:

Process: Foam Molding Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Foam grades tested with foamed parts with a 10% weight reduction relative to unfoamed parts. Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-PPX-SF2-Modified-PPO-Structural-Foam-Grade-Standard-Flow-Unverified-Data.php

Physical Properties	Metric	English	Comments
Density	1.09 g/cc	0.0394 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0060 - 0.0090 cm/cm	0.0060 - 0.0090 in/in	ASTM D955
Melt Flow	25 - 45 g/10 min	25 - 45 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	29.0 MPa	4200 psi	ASTM D638
Tensile Strength, Yield	27.6 MPa	4000 psi	ASTM D638
Flexural Strength	50.3 MPa	7300 psi	ASTM D790
Flexural Modulus	2.07 GPa	300 ksi	ASTM D790
Izod Impact, Unnotched	2.14 J/cm	4.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	82.2 °C	180 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	76.7 °C	170 °F	ASTM D648
Flammability, UL94	V-0	V-0	1/8 in

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	232 - 260 °C	450 - 500 °F	
Middle Barrel Temperature	271 - 304 °C	520 - 580 °F	
Front Barrel Temperature	271 - 304 °C	520 - 580 °F	

Melt Temperature Processing Properties	271 - 304 °C Metric	520 - 580 °F English	Comments
Mold Temperature	65.6 - 82.2 °C	150 - 180 °F	
Drying Temperature	71.1 - 82.2 °C	160 - 180 °F	
Dry Time	3 - 4 hour	3 - 4 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China