

Polymer Resources TP-FRG7.5 Polybutylene Terephthalate, 7 1/2 % Glass Reinforced, Flame Retardant

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 10% Glass Fiber Filled , Polybutylene Terephthalate (PBT), Glass Fiber Filled, Flame Retardant

Material Notes:

Polybutylene Terephthalate, 7 1/2 % Glass Reinforced, Flame Retardant Process: Injection Molding Notes: All physical, mechanical and thermal testing conducted on 1/8-inch thick, un-pigmented, test samples. Information provided by Polymer Resources Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polymer-Resources-TP-FRG75-Polybutylene-Terephthalate-7-12-Glass-Reinforced-Flame-Retardant.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.45 g/cc	1.45 g/cc	ASTM D792
Linear Mold Shrinkage	0.0060 - 0.0090 cm/cm	0.0060 - 0.0090 in/in	ASTM D955
Melt Flow	10 - 20 g/10 min @Load 2.16 kg, Temperature 250 °C	10 - 20 g/10 min @Load 4.76 lb, Temperature 482 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	82.7 MPa	12000 psi	ASTM D638
Tensile Strength, Yield	82.7 MPa	12000 psi	ASTM D638
Flexural Strength	121 MPa	17500 psi	ASTM D790
Flexural Modulus	3.45 GPa	500 ksi	ASTM D790
Izod Impact, Notched	0.267 J/cm @Temperature 22.8 °C	0.500 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	199 °C	390 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	149 °C	300 °F	ASTM D648
Flammability, UL94	V-0 @Thickness 1.59 mm	V-0 @Thickness 0.0626 in	
	V-0 @Thickness 3.17 mm	V-0 @Thickness 0.125 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	238 - 254 °C	460 - 490 °F	
Middle Barrel Temperature	243 - 260 °C	470 - 500 °F	
Front Barrel Temperature	249 - 266 °C	480 - 510 °F	
Melt Temperature	249 - 266 °C	480 - 510 °F	
Mold Temperature	65.6 - 87.8 °C	150 - 190 °F	
Drying Temperature	116 - 121 °C	240 - 250 °F	
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Vent	0.0005	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China