

Polyplastic TechnoTep A® 65 A Thermoplastic Elastomer, Mineral Filled

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Low mineral filled, good flexibility Information provided by PolyPlastic Group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyplastic-TechnoTep-A-65-A-Thermoplastic-Elastomer-Mineral-Filled.php

Physical Properties	Metric	English	Comments
Density	1.00 g/cc	0.0361 lb/in³	ISO 1183
Melt Flow	40 g/10 min	40 g/10 min	ISO 1133
	@Load 5.00 kg, Temperature 190 °C	@Load 11.0 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	ISO 868
Tensile Strength at Break	4.70 MPa	682 psi	ISO 37
Elongation at Break	600 %	600 %	ISO 37

Processing Properties	Metric	English	Comments
Melt Temperature	140 - 190 °C	284 - 374 °F	
Mold Temperature	10.0 - 30.0 °C	50.0 - 86.0 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China