

Polyplastics Duracon® CH-20 Acetal Co-polymer (POM), Conductive, CF reinforced, Wear resistance

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Carbon Fiber Filled

Material Notes:

DURACON® is a crystalline thermoplastic acetal copolymer. The primary raw material trioxane, a trimer of formaldehyde. The thermoplastic adopts a copolymer structure in which polyoxymethylene (-C-O) and carbon-carbon (-C-C- bond) comonomer groups are incorporated into its main chain. Therefore the copolymer has superior chemical and thermal stability, compared with acetal homopolymer. Acetal co-polymer is well-balanced in terms of mechanical, chemical and thermal properties, and its superior moldability allows it to be widely employed in various industrial fields. Information provided by PolyPlastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyplastics-Duracon-CH-20-Acetal-Co-polymer-POM-Conductive-CF-reinforced-Wear-resistance.php

Physical Properties	Metric	English	Comments
Density	1.47 g/cc	0.0531 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	144 MPa	20900 psi	ISO 527-1, 2
Elongation at Break	1.5 %	1.5 %	ISO 527-1, 2
Tensile Modulus	14.0 GPa	2030 ksi	ISO 527-1, 2
Flexural Strength	205 MPa	29700 psi	ISO 178
Flexural Modulus	12.0 GPa	1740 ksi	ISO 178
Charpy Impact, Notched	0.500 J/cm ²	2.38 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear	10.0 µm/m-°C	5.56 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
CTE, linear, Transverse to Flow	90.0 µm/m-°C	50.0 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
Deflection Temperature at 1.8 MPa (264 psi)	163 °C	325 °F	ISO 75-1, 2
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	Metric	English	Comments
Surface Resistance	100 ohm	100 ohm	IEC 60093

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China