

Polyplastics Duracon® SF-15 Acetal Co-polymer (POM), High impact, Flexible

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Impact Modified

Material Notes:

DURACON® is a crystalline thermoplastic acetal copolymer. The primary raw material trioxane, a trimer of formaldehyde. The thermoplastic adopts a copolymer structure in which polyoxymethylene (-C-O) and carbon-carbon (-C-C- bond) comonomer groups are incorporated into its main chain. Therefore the copolymer has superior chemical and thermal stability, compared with acetal homopolymer. Acetal co-polymer is well-balanced in terms of mechanical, chemical and thermal properties, and its superior moldability allows it to be widely employed in various industrial fields. Information provided by PolyPlastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyplastics-Duracon-SF-15-Acetal-Co-polymer-POM-High-impact-Flexible.php

Physical Properties	Metric	English	Comments
Density	1.33 g/cc	0.0480 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	38.0 MPa	5510 psi	ISO 527-1, 2
Elongation at Break	100 %	100 %	ISO 527-1, 2
Tensile Modulus	1.70 GPa	247 ksi	ISO 527-1, 2
Flexural Strength	51.0 MPa	7400 psi	ISO 178
Flexural Modulus	1.50 GPa	218 ksi	ISO 178
Charpy Impact, Notched	1.50 J/cm ²	7.14 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear	130 µm/m-°C @Temperature 23.0 - 55.0 °C	72.2 µin/in-°F @Temperature 73.4 - 131 °F	ISO 11359-2
CTE, linear, Transverse to Flow	130 µm/m-°C @Temperature 23.0 - 55.0 °C	72.2 µin/in-°F @Temperature 73.4 - 131 °F	ISO 11359-2
Deflection Temperature at 1.8 MPa (264 psi)	72.0 °C	162 °F	ISO 75-1, 2
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	3.00e+13 ohm-cm	3.00e+13 ohm-cm	IEC 60093

Electrical Properties	1.00e+14 ohm Metric	1.00e+14 ohm English	IEC 60093 Comments
Dielectric Strength	18.0 kV/mm	457 kV/in	IEC 60243-1

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China