

## Polyplastics Duranex® 2016 Polybutylene Terephthalate (PBT), Standard, FR, UL approved regrind 50%

Category: Polymer, Thermoplastic, Polyester, TP, Polybutylene Terephthalate (PBT), Polybutylene Terephthalate (PBT), Unreinforced, Molded

## **Material Notes:**

DURANEX® is a crystalline thermoplastic based on polybutylene terephthalate (PBT) that can be readily strengthened, modified, or otherwise performance enhanced through the addition of glass fibers or other inorganic filler additives. Various grades are available, including flame-retardant, reinforced, and impact-resistant grades. DURANEX®, due to its mechanical strength, heat stability, electrical resistivity and wear and abrasion-resistance, offers great potential as a well-balanced, highly reliable material, having a wide variety of applications including electronic / electro-mechanical and automobile parts and various other functional parts. DURANEX® also assures moldability, dimensional stability, glossy surfaces and various fabrication capabilities providing higher added value.Information provided by PolyPlastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_Polyplastics-Duranex-2016-Polybutylene-Terephthalate-PBT-Standard-FR-UL-approved-regrind-50.php

Physical Properties	Metric	English	Comments
Density	1.43 g/cc	0.0517 lb/in³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	59.0 MPa	8560 psi	ISO 527-1, 2
Elongation at Break	35 %	35 %	ISO 527-1,2
Flexural Strength	98.0 MPa	14200 psi	ISO 178
Flexural Modulus	2.85 GPa	413 ksi	ISO 178
Charpy Impact, Notched	0.460 J/cm²	2.19 ft-lb/in <sup>2</sup>	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	82.0 °C	180 °F	ISO 75-1,2
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	4.00e+16 ohm-cm	4.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+17 ohm	1.00e+17 ohm	IEC 60093
Dielectric Strength	24.0 kV/mm	610 kV/in	IEC 60243-1
Comparative Tracking Index	250 V	250 V	IEC 60112



## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China