

Polyplastics Duranex® CN7130 Polybutylene Terephthalate (PBT), Low friction, Low wear, GF filled

Category: Polymer, Thermoplastic, Polyester, TP, Polybutylene Terephthalate (PBT), Polybutylene Terephthalate (PBT), Glass Filled, Impact Modified

Material Notes:

DURANEX® is a crystalline thermoplastic based on polybutylene terephthalate (PBT) that can be readily strengthened, modified, or otherwise performance enhanced through the addition of glass fibers or other inorganic filler additives. Various grades are available, including flame-retardant, reinforced, and impact-resistant grades. DURANEX®, due to its mechanical strength, heat stability, electrical resistivity and wear and abrasion-resistance, offers great potential as a well-balanced, highly reliable material, having a wide variety of applications including electronic / electro-mechanical and automobile parts and various other functional parts. DURANEX® also assures moldability, dimensional stability, glossy surfaces and various fabrication capabilities providing higher added value.Information provided by PolyPlastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyplastics-Duranex-CN7130-Polybutylene-Terephthalate-PBT-Low-friction-Low-wear-GF-filled.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|---------------|----------|
| Density | 1.75 g/cc | 0.0632 lb/in³ | ISO 1183 |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|-------------------------|----------------------------|--------------|
| Tensile Strength, Ultimate | 123 MPa | 17800 psi | ISO 527-1,2 |
| Elongation at Break | 1.8 % | 1.8 % | ISO 527-1, 2 |
| Flexural Strength | 195 MPa | 28300 psi | ISO 178 |
| Flexural Modulus | 10.46 GPa | 1517 ksi | ISO 178 |
| Charpy Impact, Notched | 0.810 J/cm ² | 3.85 ft-lb/in ² | ISO 179/1eA |

| Thermal Properties | Metric | English | Comments |
|---|--------|---------|------------|
| Deflection Temperature at 1.8 MPa (264 psi) | 211 °C | 412 °F | ISO 75-1,2 |
| Flammability, UL94 | V-0 | V-0 | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China