

Polyplastics FR-PET® C3030FA Glass Fiber Reinforced Polyethylene Terephthalate (GF-PET), Slow burning, General purpose

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), Glass/Mineral Reinforced

Material Notes:

Information provided by PolyPlastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyplastics-FR-PET-C3030FA-Glass-Fiber-Reinforced-Polyethylene-Terephthalate-GF-PET-Slow-burning-General-purpose.php

Physical Properties	Metric	English	Comments
Density	1.60 g/cc	0.0578 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	147 MPa	21300 psi	ISO 527-1, 2
Elongation at Break	1.8 %	1.8 %	ISO 527-1, 2
Flexural Strength	241 MPa	35000 psi	ISO 178
Flexural Modulus	10.4 GPa	1510 ksi	ISO 178
Charpy Impact, Notched	0.830 J/cm ²	3.95 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	238 °C	460 °F	ISO 75-1, 2
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	6.00e+16 ohm-cm	6.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+17 ohm	1.00e+17 ohm	IEC 60093
Dielectric Strength	21.0 kV/mm	533 kV/in	IEC 60243-1
Comparative Tracking Index	200 V	200 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China