

Polyram Bondyram® 4108 Maleic Anhydride Modified Linear Low Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , Anhydride-Modified Polyethylene

Material Notes:

Recommended as coupling agent for PE composites filled with high filler content for halogen Free Flame Retarded cables composites. Information provided by Polyram.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-Bondyram-4108-Maleic-Anhydride-Modified-Linear-Low-Density-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.918 g/cc	0.0332 lb/in³	ISO 1183
Melt Flow	1.0 g/10 min @Load 2.16 kg, Temperature 190 °C	1.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China