

Polyram PlusTek PB340S6 Nylon 6, 30% Glass beads

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Glass Bead Filled

Material Notes:

30% glass beads reinforced polyamide 6 for injection molding applications Information provided by Polyram Ram On Ind.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-PlusTek-PB340S6-Nylon-6-30-Glass-beads.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	DIN 53479
Water Absorption	5.8 %	5.8 %	DIN 53495
Moisture Absorption at Equilibrium	1.8 %	1.8 %	50%RH; DIN 53714
Linear Mold Shrinkage	0.0080 - 0.010 cm/cm	0.0080 - 0.010 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	70.0 MPa	10200 psi	ASTM-D638
Elongation at Break	4.0 %	4.0 %	ASTM-D638
Flexural Strength	120 MPa	17400 psi	ASTM D790
Flexural Modulus	3.60 GPa	522 ksi	ASTM-D790
Izod Impact, Notched	0.500 J/cm @Temperature 23.0 °C	0.937 ft-lb/in @Temperature 73.4 °F	ASTM-D256

Thermal Properties	Metric	English	Comments
Melting Point	218 °C	424 °F	
Maximum Service Temperature, Air	80.0 °C	176 °F	Continuous Use
	180 °C	356 °F	Short peaks operation
Deflection Temperature at 0.46 MPa (66 psi)	190 °C	374 °F	DIN 53461
Deflection Temperature at 1.8 MPa (264 psi)	90.0 °C	194 °F	DIN 53461
Flammability, UL94	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity Electrical Properties	1.00e+12 ohm-cm Metric	1.00e+12 ohm-cm English	DIN 53482 Comments
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	DIN 53482
Dielectric Constant	3.8	3.8	VDE 0303/4
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	80.0 kV/mm	2030 kV/in	VDE 0303/4

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China