

Polyram PlusTek RA300G6 Nylon 6.6, 30% Glass Fiber

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

30% glass fiber reinforced polyamide 6.6 for injection molding applicationsInformation provided by Polyram Ram On Ind.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-PlusTek-RA300G6-Nylon-66-30-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in ³	DIN 53479
Water Absorption	0.80 %	0.80 %	DIN 53495
Linear Mold Shrinkage	0.0020 - 0.0030 cm/cm	0.0020 - 0.0030 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	>= 150 MPa	>= 21800 psi	ASTM-D638
Elongation at Break	3.0 %	3.0 %	ASTM-D638
Flexural Strength	>= 210 MPa	>= 30500 psi	ASTM D790
Flexural Modulus	>= 7.50 GPa	>= 1090 ksi	ASTM-D790
Izod Impact, Notched	>= 0.750 J/cm @Temperature 23.0 °C	>= 1.41 ft-lb/in @Temperature 73.4 °F	ASTM-D256

Thermal Properties	Metric	English	Comments
Melting Point	256 °C	493 °F	
Deflection Temperature at 0.46 MPa (66 psi)	>= 240 °C	>= 464 °F	DIN 53461
Deflection Temperature at 1.8 MPa (264 psi)	>= 210 °C	>= 410 °F	DIN 53461
Flammability, UL94	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China