

Polyram RamShine PAS702 ASA, UV Stabilized

Category : Polymer , Thermoplastic , ASA Polymer , Acrylonitrile/Styrene/Acrylate (ASA), Unreinforced, Molded

Material Notes:

UV stabilized, general purpose, injection molding ASA. Information provided by Polyram.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-RamShine-PAS702-ASA-UV-Stabilized.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.0050 cm/cm	0.0050 in/in	ISO 2577
Melt Flow	25 g/10 min	25 g/10 min	ISO 1133
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	45.0 MPa	6530 psi	ISO 527
Elongation at Break	60 %	60 %	ISO 527
Tensile Modulus	2.20 GPa	319 ksi	ISO 527
Flexural Strength	70.0 MPa	10200 psi	ISO 178
Flexural Modulus	2.00 GPa	290 ksi	ISO 178
Izod Impact, Notched (ISO)	10.0 kJ/m ²	4.76 ft-lb/in ²	ISO 180

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	101 °C	214 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	96.0 °C	205 °F	ISO 75

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	IEC 60093

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China