

Polyram RamTal PM3013G4 Acetal, 20% Glass Fiber

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, 20% Glass Fiber Reinforced

Material Notes:

20% Glass fiber reinforced polyacetal for injection molding applicationsInformation provided by Polyram Ram On Ind.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-RamTal-PM3013G4-Acetal-20-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.54 g/cc	0.0556 lb/in ³	DIN 53479
Water Absorption	0.20 %	0.20 %	DIN 53495
Linear Mold Shrinkage	0.0050 cm/cm	0.0050 in/in	
Melt Flow	5.0 g/10 min @Load 2.16 kg, Temperature 190 °C	5.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	90.0 MPa	13100 psi	ASTM-D638
Elongation at Break	2.5 %	2.5 %	ASTM-D638
Flexural Strength	120 MPa	17400 psi	ASTM-D790
Flexural Modulus	3.20 GPa	464 ksi	ASTM-D790
Izod Impact, Notched	0.650 J/cm @Temperature 23.0 °C	1.22 ft-lb/in @Temperature 73.4 °F	ASTM-D256

Thermal Properties	Metric	English	Comments
Melting Point	165 °C	329 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	DIN 53482
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	DIN 53482
Dielectric Strength	20.0 kV/mm	508 kV/in	VDE 0303/4

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China