

Polyram RamTough PZ307G2 Polycarbonate, 10% Glass Fiber

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, 10% Glass Filled

Material Notes:

10% glass fiber reinforced, UV stabilized polycarbonate for injection molding applications Information provided by Polyram Ram On Ind.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-RamTough-PZ307G2-Polycarbonate-10-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.27 g/cc	0.0459 lb/in ³	DIN 53479
Water Absorption	0.090 %	0.090 %	DIN 53495
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	
Melt Flow	10 g/10 min @Load 1.20 kg, Temperature 300 °C	10 g/10 min @Load 2.65 lb, Temperature 572 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	65.0 MPa	9430 psi	ASTM-D638
Elongation at Break	8.0 %	8.0 %	ASTM-D638
Flexural Strength	120 MPa	17400 psi	ASTM D790
Flexural Modulus	3.70 GPa	537 ksi	ASTM-D790
Izod Impact, Notched	1.20 J/cm @Temperature 23.0 °C	2.25 ft-lb/in @Temperature 73.4 °F	ASTM-D256

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.220 W/m-K	1.53 BTU-in/hr-ft ² -°F	DIN 52612
Deflection Temperature at 0.46 MPa (66 psi)	145 °C	293 °F	DIN 53461
Deflection Temperature at 1.8 MPa (264 psi)	145 °C	293 °F	DIN 53461
Flammability, UL94	V-1 @Thickness 3.00 mm	V-1 @Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	DIN 53482

Surface Resistance Electrical Properties	1.00e+14 ohm Metric	1.00e+14 ohm English	DIN 53482 Comments
Dielectric Constant	3.2	3.2	VDE 0303/4
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	30.0 kV/mm	762 kV/in	VDE 0303/4

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China