

Polyram RamTough PZ307G6 Polycarbonate, 30% Glass Fiber, UV Stabilized

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, 30% Glass Filled

Material Notes:

30% glass fiber reinforced polycarbonate, UV stabilized, for injection molding applications. Information provided by Polyram.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polyram-RamTough-PZ307G6-Polycarbonate-30-Glass-Fiber-UV-Stabilized.php

Physical Properties	Metric	English	Comments
Density	1.16 g/cc	0.0419 lb/in ³	ISO 1183
Water Absorption at Saturation	0.10 %	0.10 %	ISO 62
Linear Mold Shrinkage	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	ISO 2577
Melt Flow	8.0 g/10 min @Load 1.20 kg, Temperature 300 °C	8.0 g/10 min @Load 2.65 lb, Temperature 572 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	120 MPa	17400 psi	ISO 527
Elongation at Break	2.5 %	2.5 %	ISO 527
Tensile Modulus	6.50 GPa	943 ksi	ISO 527
Flexural Strength	220 MPa	31900 psi	ISO 178
Flexural Modulus	7.80 GPa	1130 ksi	ISO 178
Izod Impact, Notched (ISO)	12.0 kJ/m ²	5.71 ft-lb/in ²	ISO 180

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	140 °C	284 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	135 °C	275 °F	ISO 75
Flammability, UL94	V-2 @Thickness 3.00 mm	V-2 @Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	IEC 60093
Dielectric Strength	30.0 kV/mm	762 kV/in	IEC 60250

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China