

Polystrand ThermoBallistic™ TBS8010X X-Ply Cross-Ply Polypropylene-Glass Composite

Category: Polymer, Tape, Thermoplastic, Polypropylene (PP)

Material Notes:

2-Ply with Fiber Orientation at 0° & 90°.Polystrand ThermoBallistic laminates combine continuous S-Glass (ThermoBallistic-S™) structural fibers with a proprietary polypropylene thermoplastic polymers to form sheets, ribbons or tapes that can be subsequently molded to create end-use applications including ballistic and blast panels to protect troops, vehicles, equipment and buildings. The Polystrand materials and process technologies combine continuous structural fibers with an energy-dissipating matrix of thermoplastic polymer. This results in a reinforced thermoplastic composite that has many advantages compared to traditional, more brittle thermosetting polymer composites in ballistic panels. The many performance benefits of Polystrand ThermoBallistic materials include:Exceptional Energy Management Properties (ballistic, blast and high strain-to-failure)Improved V50 Performance Against a 30 Caliber FSP (ThermoBallistic E)Lighter Weight (automotive, aircraft and defense applications)X-Ply™ 0/90 Laminates up to 50" x 100" (1.27m x 2.54m) and rolls100% Recyclable (no material waste)Reduced Molding Cycles (higher productivity and lower cost)Re-Formable (panels can be reconfigured multiple times)Design Flexibility (fiber selection and fiber orientation)Information provided by Polystrand.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polystrand-ThermoBallistic-TBS8010X-X-Ply-Cross-Ply-Polypropylene-Glass-Composite.php

Physical Properties	Metric	English	Comments
Density	1.88 g/cc	0.0679 lb/in³	
Filler Content	80 %	80 %	S-Glass; ASTM D2584
Thickness	330 microns	13.0 mil	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China