

## Precision Polymer Engineering Q75B Polyurethane Rubber

Category : Polymer , Thermoset , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Sulphur cured, Polyurethane Rubber, 65-75 °IRHD. Polyester-based urethane. To meet ASTM line call-out M5BG728, B14, E014, E034.

ASTM & ISO designation = AU.Applications: Excellent abrasion resistance and tensile strength, with fluid compatibility approaching that of NBR. Polyurethane seals provide outstanding performance in hydraulic systems, which are prone to abrasive contamination and high shock loads. Good resistance to weathering and ozone but poor against water and high temperature.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Precision-Polymer-Engineering-Q75B-Polyurethane-Rubber.php](http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-Q75B-Polyurethane-Rubber.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	°IRHD; ASTM D1415
	85	85	°IRHD, +15 change after 70 hours @ 100°C; ASTM D1415
Tensile Strength, Yield	22.4 MPa	3250 psi	-20% change after 70 hours @ 100°C; ASTM D412
	28.0 MPa	4060 psi	ASTM D412
Elongation at Break	240 %	240 %	-40% change after 70 hours @ 100°C; ASTM D412
	400 %	400 %	ASTM D412
Compression Set	25 %	25 %	70 hours @ 100°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	100 °C	212 °F	
Minimum Service Temperature, Air	-35.0 °C	-31.0 °F	Non-brittle after 3 minutes
	-30.0 °C	-22.0 °F	
Flash Point	>= 204 °C	>= 399 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China