

Precision Polymer Engineering R60D Natural Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Natural Rubber, 55-65 °IRHD. Formulated to Defence Standard 93-30, Type QX, Grade 60 (NRQX60). Applications: Natural rubber offers low compression set, high tensile strength, high resilience and excellent resistance to tear and abrasion. The designation `Type QX` indicates that the material is suitable for certain applications where a high degree of compatibility with explosives is a requirement. However, compatibility with all explosives in all environments has not been established and design authorities should seek advice on particular applications from the Director, Defence Research Agency (Military Division), Fort Halstead, Sevenoaks, Kent, TN14 7BP.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Precision-Polymer-Engineering-R60D-Natural-Rubber.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	°IRHD; ASTM D1415
	60 - 64	60 - 64	°IRHD, -0/+4 change after 168 hours @ 70°C; ASTM D1415
Tensile Strength, Yield	12.6 MPa	1830 psi	- 10% change after 168 hours @ 70°C; ASTM D412
	14.0 MPa	2030 psi	ASTM D412
Elongation at Break	382.5 %	382.5 %	- 15% change after 168 hours @ 70°C; ASTM D412
	450 %	450 %	ASTM D412
Compression Set	30 %	30 %	24 hours @ 70°C; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	100 °C	212 °F	
Minimum Service Temperature, Air	-50.0 °C	-58.0 °F	
Flash Point	>= 300 °C	>= 572 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China