

Premix Thermoplastics PRETHERM TPE 1075 Thermoplastic Elastomer, Boron Nitride / SEBS compound

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

PRETHERM TPE 1075 is a thermoplastic elastomer based highly thermally conductive compound intended primarily for heat dissipation. It can be used as gap filler between processor and heat sink or co-molded into plastic shell. Thermal conductivity is achieved with Boron nitride which is highly thermally conductive and electrically isolating. PRETHERM TPE 1075 can be injection-molded like an ordinary thermoplastic elastomer thus giving great new possibilities in gasket design and mass production. It has adhesion to selected thermoplastics and metal contacts are also arranged. It can be used in co-injection molding e.g. molding the gasket directly in the phone casing. Recyclability is an added value. The material is silicone free. The electronics industry is moving towards smaller devices with an increasing amount of special features. The smaller the device the more attention should be paid to controlling the excess heat. Cost Savings Through a Simplified Production Process: Traditionally the silicon-based compounds and glues are used as an intermediate heat conductor from circuit board to metal plate. When choosing PRETHERM TPE compound instead, the production process will be simplified and accelerated radically; PRETHERM TPE can be co-moulded with metal without using any primers. This results in a competitive advantage by reducing the production costs. PRETHERM TPE compounds are insulative and non-migrating and can therefore be placed directly into contact with sensitive electronics without the risk of short-circuits. Design and Processing: Production using normal thermoplastic processing methods; injection molding and extrusion Easy processability enables product designs with complex shapes and sizes Mass-production friendly; fast cycle times, no need for vulcanisation nor primers Recyclable and RoHS compliant Applications: Heat sink, gap filler between metal and electric component in mobile phones, mobile phone base stations and other electronics as well as military application. Information from Premix OY

Order this product through the following link:

http://www.lookpolymers.com/polymer_Premix-Thermoplastics-PRETHERM-TPE-1075-Thermoplastic-Elastomer-Boron-Nitride-SEBS-compound.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|---------------------------|----------|
| Density | 1.60 g/cc | 0.0578 lb/in ³ | |

| Mechanical Properties | Metric | English | Comments |
|-------------------------|-------------------------------------------------|------------------------------------------------|--------------|
| Hardness, Shore A | 75 | 75 | ISO 868 |
| Tensile Strength | 1.80 MPa | 261 psi | ISO 37 |
| Tensile Strength, Yield | 1.80 MPa | 261 psi | ISO 37 |
| Elongation at Break | 28 % | 28 % | ISO 37 |
| Elongation at Yield | 28 % | 28 % | ISO 37 |
| Compression Set | 81 % @Temperature 85.0 °C, Time 86400 sec | 81 % @Temperature 185 °F, Time 24.0 hour | ISO 815:1991 |

| Thermal Properties | Metric | English | Comments |
|------------------------|-------------|------------------------------------|----------|
| Specific Heat Capacity | 1.25 J/g-°C | 0.299 BTU/lb-°F | |
| Thermal Conductivity | 5.30 W/m-K | 36.8 BTU-in/hr-ft ² -°F | Hot Disk |

| Electrical Properties | Metric | English | Comments |
|-----------------------|-----------------|-----------------|-----------|
| Volume Resistivity | 1.00e+13 ohm-cm | 1.00e+13 ohm-cm | ISO D-257 |

| Processing Properties | Metric | English | Comments |
|-------------------------|--------------------|----------------------|-------------------------------------------------------------------------------------------------------------------|
| Rear Barrel Temperature | 200 °C | 392 °F | Zone 1 |
| | 200 °C | 392 °F | Zone 2 |
| | 200 °C | 392 °F | Zone 3 |
| | 200 °C | 392 °F | Zone 4 |
| | 200 °C | 392 °F | Zone 5 |
| Nozzle Temperature | 200 °C | 392 °F | |
| Mold Temperature | 70.0 °C | 158 °F | Moulding a 6 gram (shot weight) gasket with a 50 ton injection moulding machine having a screw diameter of 25[mm] |
| Injection Velocity | 10.0 - 25.0 mm/sec | 0.394 - 0.984 in/sec | Molding a 6 gram (shot weight) gasket with a 50 ton injection molding machine; screw diameter of 25 mm |
| Drying Temperature | <= 60.0 °C | <= 140 °F | Pre-drying |
| Dry Time | 3 hour | 3 hour | |
| Moisture Content | <= 0.040 % | <= 0.040 % | when produced |
| Hold Pressure | 0.000 MPa | 0.000 psi | |
| Back Pressure | 0.300 MPa | 43.5 psi | Moulding a 6 gram (shot weight) gasket with a 50 ton injection moulding machine having a screw diameter of 25[mm] |
| Cycle Time - Cooling | 25 sec | 25 sec | |
| Shelf Life | 12.0 Month | 12.0 Month | Normal Storing Conditions |

| Descriptive Properties | Value | Comments |
|------------------------|---------|----------|
| Appearance | Granule | |

| Colour Descriptive Properties | White Value | Comments |
|-----------------------------------------|---------------------------|----------|
| Holding Time(s) | 5 | |
| Injection time (s) | 0.7 | |
| Plasticising speed | 25-80% of Max 480 rev/min | |
| Thermal Diffusivity(mm ² /s) | 2.6 | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China