

Process Technologies Inc BUNA-N/Metal Metal Detectable Sanitary Gasket

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

BUNA-N/Metal should be considered for use with oils and animal fats. BUNA-N/Metal should be considered for use with oils and animal fats. This material is FDA compliant and has good compression set characteristics. BUNA-N/Metal does have a limited temperature range which precludes its use in many applications. Information provided by Process Technologies Inc

Order this product through the following link:

http://www.lookpolymers.com/polymer_Process-Technologies-Inc-BUNA-NMetal-Metal-Detectable-Sanitary-Gasket.php

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	93.33 °C	200.0 °F	
Minimum Service Temperature, Air	-34.44 °C	-29.99 °F	

Descriptive Properties	Value	Comments
Compatibility for Chemicals	Acetone	Not Recommended
	Ammonia	Good
	Hydrochloric Acid	Not Recommended
	Hydrofluoric Acid	Not Recommended
	Hydrogen Peroxide	Good
	Isopropyl Alcohol	Good
	Nitric Acid	Not Recommended
	Phosphoric Acid	Good
	Sodium Hydroxide	Good
	Sodium Hypochlorite	Good
	Steam to 400°F (204°C)	Not Recommended
	Sulfuric Acid	Limited

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China