

Quadrant EPP Cestlite™ ASTL Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Injection Molded

Material Notes:

Data provided by Quadrant Engineering Plastic Products for polymers in their European product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Quadrant-EPP-Cestlite-ASTL-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.950 g/cc	0.0343 lb/in ³	ISO 1183
Water Absorption	0.050 %	0.050 %	immersion

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	61	61	after 15 sec.; ISO 868
	63	63	after 3 sec.; ISO 868
Ball Indentation Hardness	37.0 MPa	5370 psi	ISO 2039-1
Tensile Strength, Yield	20.0 MPa	2900 psi	ISO 527
Elongation at Break	>= 50 %	>= 50 %	ISO 527
Elongation at Yield	15 %	15 %	ISO 527
Tensile Modulus	0.770 GPa	112 ksi	ISO 527
Compressive Yield Strength	5.00 MPa	725 psi	at 1% nominal strain; ISO 604
	9.00 MPa	1310 psi	at 2% nominal strain; ISO 604
	15.0 MPa	2180 psi	at 5% nominal strain; ISO 604
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
Charpy Impact, Notched	8.00 J/cm ²	38.1 ft-lb/in ²	Partial Break; ISO 179/1eA
Abrasion	85	85	Relative loss per DSM internal test (CESTILENE HD 1000 = 100)

Thermal Properties	Metric	English	Comments
CTE, linear	175 - 225 µm/m-°C	97.2 - 125 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Thermal Conductivity	0.400 W/m-K	2.78 BTU-in/hr-ft ² -°F	
Melting Point	130 - 135 °C	266 - 275 °F	ISO 3146; DSC, 10°C/min

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	120 °C	248 °F	20,000 hours continuous for short periods
Deflection Temperature at 1.8 MPa (264 psi)	42.0 °C	108 °F	ISO 75 method A
Vicat Softening Point	83.0 °C	181 °F	ISO 306
Minimum Service Temperature, Air	-150 °C	-238 °F	
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
Oxygen Index	<= 20 %	<= 20 %	ISO 4589

Electrical Properties	Metric	English	Comments
Electrical Resistivity	<= 1.00e+6 ohm-cm	<= 1.00e+6 ohm-cm	IEC 93
Surface Resistance	<= 1.00e+6 ohm	<= 1.00e+6 ohm	IEC 93

Descriptive Properties	Value	Comments
Color	black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China