

Quadrant EPP Duratron® PAI T4501 Polyamide-imide, compression molded bearing grade (ASTM Product Data Sheet)

Category : Polymer , Thermoplastic , Polyamide-imide (PAI) , Polyamide-Imide, Molded

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Quadrant-EPP-Duratron-PAI-T4501-Polyamide-imide-compression-molded-bearing-grade-ASTM-Product-Data-Sheet.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.45 g/cc	1.45 g/cc	ASTM D792
Water Absorption	0.30 %	0.30 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	1.5 %	1.5 %	Immersion; ASTM D570(2)

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell E	70	70	ASTM D785
Hardness, Rockwell M	106	106	ASTM D785
Hardness, Shore D	90	90	ASTM D2240
Tensile Strength	68.9 MPa	10000 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Tensile Modulus	3.03 GPa	440 ksi	ASTM D638
Flexural Strength	138 MPa	20000 psi	ASTM D790
Flexural Modulus	4.48 GPa	650 ksi	ASTM D790
Compressive Strength	110 MPa	16000 psi	10% Def.; ASTM D695
Compressive Modulus	2.48 GPa	359 ksi	ASTM D695
Izod Impact, Notched	0.267 J/cm	0.500 ft-lb/in	ASTM D256 Type A
Coefficient of Friction, Dynamic	0.20	0.20	Dry vs. Steel; QTM55007
K (wear) Factor	302 x 10 ⁻⁸ mm ³ /N-M	150 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	QTM 55010
Limiting Pressure Velocity	0.788 MPa-m/sec	22500 psi-ft/min	4:1 safety factor; QTM 55007

Thermal Properties	Metric	English	Comments
CTE, linear	36.0 µm/m-°C	20.0 µin/in-°F	ASTM E831

Thermal Properties	Metric @Temperature -40.0 - 145 °C	English @Temperature -40.0 - 309 °F	Comments
Thermal Conductivity	0.533 W/m-K	3.70 BTU-in/hr-ft²-°F	ASTM F433
Maximum Service Temperature, Air	260 °C	500 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	279 °C	534 °F	ASTM D648
Glass Transition Temp, Tg	275 °C	527 °F	ASTM D3418
Flammability, UL94	V-0	V-0	1/8 inch (Estimated Rating)

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	>= 1.00e+13 ohm	>= 1.00e+13 ohm	EOS/ESD S11.11
Dielectric Constant	6.0 @Frequency 1e+6 Hz	6.0 @Frequency 1e+6 Hz	ASTM D150
Dissipation Factor	0.042 @Frequency 1e+6 Hz	0.042 @Frequency 1e+6 Hz	ASTM D150

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
Canada AG	No	No	
FDA	No	No	
NSF	No	No	
USDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Limited	Limited	
Acids, Weak	Acceptable	Acceptable	
Alcohols	Acceptable	Acceptable	
Alkalies, Strong (pH 11-14)	Unacceptable	Unacceptable	
Alkalies, Weak	Limited	Limited	
Chlorinated Solvents	Acceptable	Acceptable	
Conductive / Static Dissipative	No	No	

Chemical Resistance Properties Continuous Sunlight	Metric Acceptable	English Acceptable	Comments
Hot Water / Steam	Limited	Limited	
Hydrocarbons - Aliphatic	Acceptable	Acceptable	
Hydrocarbons - Aromatic	Acceptable	Acceptable	
Inorganic Salt Solutions	Acceptable	Acceptable	
Ketones, Esters	Acceptable	Acceptable	

Descriptive Properties	Value	Comments
Machinability	6	1-10, 1=Easier to Machine

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China