

Quadrant EPP Duratron® PI D7000 PI Unfilled Polyimide (ASTM Product Data Sheet)

Category : Polymer , Thermoplastic , Polyimide, Thermoplastic

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Quadrant-EPP-Duratron-PI-D7000-PI-Unfilled-Polyimide-ASTM-Product-Data-Sheet.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.37 g/cc	1.37 g/cc	ASTM D792
Water Absorption	0.70 %	0.70 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	3.8 %	3.8 %	ASTM D570(2)

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	128	128	ASTM D785
Hardness, Shore D	90	90	ASTM D2240
Tensile Strength	121 MPa	17500 psi	ASTM D638
Elongation at Break	6.0 %	6.0 %	ASTM D638
Tensile Modulus	3.72 GPa	540 ksi	ASTM D638
Flexural Strength	172 MPa	25000 psi	ASTM D790
Flexural Modulus	3.79 GPa	550 ksi	ASTM D790
Compressive Strength	186 MPa	27000 psi	10% Deformation; ASTM D695
Compressive Modulus	2.62 GPa	380 ksi	ASTM D695
Shear Strength	110 MPa	16000 psi	ASTM D732
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	ASTM 256 Type 'A'
Coefficient of Friction, Dynamic	0.29	0.29	Dry vs. Steel; QTM 55007
K (wear) Factor	302 x 10 ⁻⁸ mm ³ /N-M	150 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	QTM55010
Limiting Pressure Velocity	0.525 MPa-m/sec	15000 psi-ft/min	4:1 safety factor; QTM 55007

Thermal Properties	Metric	English	Comments
CTE, linear	40.5 µm/m-°C	22.5 µin/in-°F	ASTM E831
	@Temperature -40.0 -	@Temperature -40.0 -	

Thermal Properties	149 °C Metric	300 °F English	Comments
Thermal Conductivity	0.216 W/m-K	1.50 BTU-in/hr-ft²-°F	ASTM E1530
Melting Point	304 °C	580 °F	
Maximum Service Temperature, Air	260 °C	500 °F	Continuous
Deflection Temperature at 1.8 MPa (264 psi)	354 °C	670 °F	ASTM D648
Glass Transition Temp, Tg	349 °C	660 °F	ASTM D3418
Flammability, UL94	V-0 @Thickness 3.17 mm	V-0 @Thickness 0.125 in	

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	>= 1.00e+13 ohm	>= 1.00e+13 ohm	EOS/ESD S11.11
Dielectric Constant	3.2 @Frequency 1.00e+6 Hz	3.2 @Frequency 1.00e+6 Hz	ASTM D150
Dielectric Strength	15.6 kV/mm	395 kV/in	Short Term; ASTM D149
Dissipation Factor	<= 0.0050 @Frequency 1.00e+6 Hz	<= 0.0050 @Frequency 1.00e+6 Hz	ASTM D150

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
Canada AG	No	No	
FDA	No	No	
NSF	No	No	
USDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Limited	Limited	
Acids, Weak	Acceptable	Acceptable	
Alcohols	Acceptable	Acceptable	

Alkalies, Strong (pH 11-14) Chemical Resistance Properties	Unacceptable Metric	Unacceptable English	Comments
Alkalies, Weak	Limited	Limited	
Chlorinated Solvents	Acceptable	Acceptable	
Conductive / Static Dissipative	No	No	
Continuous Sunlight	Limited	Limited	
Hot Water / Steam	Limited	Limited	
Hydrocarbons - Aliphatic	Acceptable	Acceptable	
Hydrocarbons - Aromatic	Acceptable	Acceptable	
Inorganic Salt Solutions	Acceptable	Acceptable	
Ketones, Esters	Acceptable	Acceptable	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China